

BAB V

KESIMPULAN & SARAN

5.1 Kesimpulan

Dari penelitian pirolisis LDPE menjadi bahan bakar cair, dapat disimpulkan bahwa :

1. Katalis yang menghasilkan produk pirolisis terbaik merupakan katalis yang memiliki situs asam bronsted terbanyak yaitu ZSM-5, diikuti Bentonite dan SiO₂.
2. Variasi suhu dalam menghasilkan produk pirolisis terbaik merupakan variasi dengan suhu 265°C.
3. % *Loading* sebesar 5 % dinilai lebih ekonomis dan lebih baik, dikarenakan perolehan produk cair tidak berbeda jauh dengan 7% dan 10%.
4. Waktu reaksi 1 jam dinilai lebih baik dan lebih ekonomis ketimbang waktu reaksi 2 jam dan 3 jam dikarenakan perolehan produk cair yang tidak berbeda jauh.

5.2 Saran

Saran untuk penelitian pirolisis LDPE menjadi bahan bakar cair adalah :

1. Padatan hasil pirolisis dapat di pirolisis kembali sehingga menghasilkan produk cair yang lebih banyak. Namun perlu dipertimbangkan cara memisahkan katalis dari produk padat. Bila dilakukan bertahap dan katalis terus ditambahkan, maka dapat terjadi deposit katalis pada reaktor.
2. Pada penelitian selanjutnya dapat lebih berfokus kepada katalis bentonite dan SiO₂

DAFTAR PUSTAKA

- [1] T. A. P. Team, "Indonesia's Plastics Waste Problems." [Online]. Available: <https://theaseanpost.com/article/indonesias-plastic-waste-problem-0>. [Accessed: 23-Oct-2019].
- [2] T. Adharsyah, "Sebegini Parah Ternyata Masalah Sampah Plastik di Indonesia." [Online]. Available: <https://www.cnbcindonesia.com/lifestyle/20190721140139-33-86420/sebegini-parah-ternyata-masalah-sampah-plastik-di-indonesia>. [Accessed: 23-Oct-2019].
- [3] A. B. Tamtomo, "Infografik Perjalanan Harga BBM di Jakarta." [Online]. Available: <https://ekonomi.kompas.com/read/2018/10/11/183130126/infografik-perjalanan-harga-bbm-di-jakarta>. [Accessed: 22-Oct-2019].
- [4] M. Sarker, "Conversion of Low Density Polyethylene (LDPE) and Polypropylene (PP) Waste Plastics into Liquid Fuel Using Thermal Cracking Process," *Br. J. Environ. Clim. Chang.*, vol. 2, no. 1, pp. 1–11, 2012.
- [5] J. Shah, M. R. Jan, F. Mabood, and F. Jabeen, "Catalytic pyrolysis of LDPE leads to valuable resource recovery and reduction of waste problems," *Energy Convers. Manag.*, vol. 51, no. 12, pp. 2791–2801, 2010.
- [6] Y. Sakata, A. Uddin, K. Muraw, and K. Koizumi, "Thermal degradation of polyethylene mixed with poly(vinyl chloride) and poly(ethyleneterephthalate)," vol. 53, pp. 111–117, 1996.
- [7] A. K. Panda, R. K. Singh, and D. K. Mishra, "Thermolysis of waste plastics to liquid fuel. A suitable method for plastic waste management and manufacture of value added products-A world prospective," *Renew. Sustain. Energy Rev.*, vol. 14, no. 1, pp. 233–248, 2009.
- [8] M. Batool, T. A. Shah, D. I. Muhammad, and B. Li, "Catalytic Pyrolysis of Low Density Polyethylene Using Cetyltrimethyl Ammonium Encapsulated Monovacant Keggin Units and ZSM-5," *Chem. Eng. News Arch.*, pp. 1–5, 2016.
- [9] F. Gao, "Pyrolysis of Waste Plastics into Fuels," *Univ. Canterbury, Christchurch*, 2010.
- [10] P. SIVAKUMAR and K. ANBARASU, "Catalytic Pyrolysis of Dairy Industrial Waste Ldpe Film Into Fuel," *Int. J. Chem. Res.*, vol. 3, no. 1, pp. 51–54, 2012.
- [11] L. Parker, "Fast Facts About Plastics Pollution." [Online]. Available: <https://www.nationalgeographic.com/news/2018/05/plastics-facts-infographics-ocean->

- pollution/. [Accessed: 23-Oct-2019].
- [12] H. Ritchie, "FAQs on Plastics." [Online]. Available: <https://ourworldindata.org/faq-on-plastics#note-3>. [Accessed: 23-Oct-2019].
- [13] A. Demirbas, "Pyrolysis of Municipal Plastic Wastes for Recovery of Gasoline-range Hydrocarbons," *J. Anal. Appl. Pyrolysis*, vol. 72, no. 1, pp. 97–102, 2004.
- [14] N. Dixon and D. R. V. Jones, "Engineering properties of municipal solid waste," *Geotext. Geomembranes*, vol. 23, no. 3, pp. 205–233, 2005.
- [15] M. Kutz, *Handbook of Materials Selection*, no. 0. New York: John Wiley & Sons, 2002.
- [16] R. J. Crawford, "Plastics Engineering," 1998. .
- [17] E. Sald and E. Vivaldo-lima, *Handbook of Polymers*. New Jersey: JOHN WILEY & SONS, INC.
- [18] S. A. Salaudeen, P. Arku, and A. Dutta, *10 Gasification of Plastic Solid Waste and Competitive Technologies*. Canada: Elsevier Inc., 2019.
- [19] American Chemistry Council, "Plastic Packaging Resins Resin Codes Descriptions Properties Product Applications Products Made with Recycled Content," p. 3, 2016.
- [20] L. Eubanks, C. H. Middlecamp, C. E. Heltzel, and S. W. Keller, *Chemistry in Context : Applying Chemistry to Society*, 6th ed. New York: McGraw-Hill, 2009.
- [21] U. S. E. P. Agency, "Learn about Dioxin." [Online]. Available: <https://www.epa.gov/dioxin/learn-about-dioxin>. [Accessed: 02-Oct-2019].
- [22] W. in E. for a C. Future, "Dangerous Health Effects of Home Burning of Plastics and Waste," pp. 1–2.
- [23] A. N. Mohamed, A. S. Tuhaiwer, and Z. S. Razzaq, "Optical Properties of Polyvinyl Chloride Doped with DCM dye Thin Films," vol. 30, pp. 45–56, 2016.
- [24] N. I. of H. S. Environmental, "Styrene," *National Institute of Environmental Health Sciences*. [Online]. Available: <http://www.niehs.nih.gov/research/resources/bioethics/whatis/index.cfm>. [Accessed: 02-Oct-2019].
- [25] M. Zubair, "Modification of Styrene-Methyl Meth Acrylate Copolymer in the Presence of Pristine and Modified Graphene By Using Microwave Irradiation," no. November 2013, 2013.
- [26] Omnexus, "The Definitive Guide to Polypropylene." [Online]. Available:

- <https://omnexus.specialchem.com/selection-guide/polypropylene-pp-plastic>. [Accessed: 02-Oct-2019].
- [27] T. Shibamoto, A. Yasuhara, and T. Katami, "Dioxin Formation from Waste Incineration," vol. 190, pp. 1–41, 2007.
- [28] G. Seaman, "Plastics by the Numbers." [Online]. Available: <https://learn.eartheasy.com/articles/plastics-by-the-numbers/>. [Accessed: 02-Oct-2019].
- [29] F. Rahadi, "Optimalkan Potensi Ekonomi Plastik." [Online]. Available: <https://www.republika.co.id/berita/nasional/umum/18/04/27/p7u15u291-optimalkan-potensi-ekonomi-plastik/>. [Accessed: 03-Oct-2019].
- [30] G. Solomons, C. Fryhle, and S. Snyder, *Organic Chemistry*, 11th ed. Danvers, 2014.
- [31] C. A. Harper and E. M. Petrie, *Plastics Materials and Processes*. New Jersey: JOHN WILEY & SONS, 2003.
- [32] J. A. Brydson, *Plastics Materials*, 7th ed. Oxford: Butterworth-Heinemann, 1999.
- [33] Omnexus, "Polyethylene." [Online]. Available: <https://omnexus.specialchem.com/selection-guide/polyethylene-plastic#LLDPE>. [Accessed: 17-Sep-2019].
- [34] F. W. Billmeyer, *Textbook of Polymer Science*, 3rd ed. New York: John Wiley & Sons, 1984.
- [35] T. Plastics, "LDPE and LLDPE Tubing." [Online]. Available: <https://www.tblplastics.com/tubing/ldpe-lldpe-tubing/>. [Accessed: 23-Sep-2019].
- [36] Action Plastics. Inc, "Typical Properties of HDPE," 2015. [Online]. Available: http://www.efunda.com/materials/alloys/alloy_home/steels_properties.cfm. [Accessed: 23-Sep-2019].
- [37] J. G. Speight, *Handbook of Industrial Hydrocarbon Processes*. 2011.
- [38] R. Rodiansono and W. Trisunaryanti, "ACTIVITY TEST AND REGENERATION OF NiMo/Z CATALYST FOR HYDROCRACKING OF WASTE PLASTIC FRACTION TO GASOLINE FRACTION," pp. 261–268, 2005.
- [39] H. Arshad, S. A. Sulaiman, Z. Hussain, Y. Naz, and F. Basrawi, "Microwave assisted pyrolysis of plastic waste for production of fuels: a review," *MATEC Web Conf.*, vol. 131, 2017.
- [40] N. Shah, J. Rockwell, and G. P. Huffman, "Conversion of waste plastic to oil: Direct

- liquefaction versus pyrolysis and hydroprocessing,” *Energy and Fuels*, vol. 13, no. 4, pp. 832–838, 1999.
- [41] S. D. A. Sharuddin, F. Abnisa, W. M. A. W. Daud, and M. K. Aroua, “Pyrolysis of plastic waste for liquid fuel production as prospective energy resource,” *IOP Conf. Ser. Mater. Sci. Eng.*, vol. 334, no. 1, 2018.
- [42] K. Lee and D. Shin, “Characteristics of liquid product from the pyrolysis of waste plastic mixture at low and high temperatures : Influence of lapse time of reaction,” vol. 27, pp. 168–176, 2007.
- [43] S. Dayana, A. Sharuddin, F. Abnisa, W. Mohd, and A. Wan, “A review on pyrolysis of plastic wastes,” *Energy Convers. Manag.*, vol. 115, pp. 308–326, 2016.
- [44] I. Publishers, “Converting Polyethylene Waste into Liquid Fuel,” 2014. [Online]. Available: <https://phys.org/news/2014-01-polyethylene-liquid-fuel.html>.
- [45] S. Budsareechai, A. J. Hunt, and Y. Ngernyen, “Catalytic pyrolysis of plastic waste for the production of liquid fuels for engines,” *RSC Adv.*, vol. 9, no. 10, pp. 5844–5857, 2019.
- [46] J. Aguado, D. P. Serrano, J. M. Escola, and E. Garagorri, “Catalytic conversion of low-density polyethylene using a continuous screw kiln reactor,” *Catal. Today*, vol. 75, no. 1–4, pp. 257–262, 2002.
- [47] I. Ahmad *et al.*, “Pyrolysis study of polypropylene and polyethylene into premium oil products,” *Int. J. Green Energy*, vol. 12, no. 7, pp. 663–671, 2015.
- [48] P. T. Williams and E. A. Williams, “Interaction of Plastics in Mixed-Plastics Pyrolysis,” no. 12, pp. 188–196, 1999.
- [49] J. Jamradloedluk and C. Lertsatitthanakorn, “Characterization and utilization of char derived from fast pyrolysis of plastic wastes,” *Procedia Eng.*, vol. 69, pp. 1437–1442, 2014.
- [50] Z. Sebestyén *et al.*, “Thermo-catalytic pyrolysis of biomass and plastic mixtures using HZSM-5,” *Appl. Energy*, vol. 207, pp. 114–122, 2017.
- [51] F. Fahed Banihani, “The Effect of Catalyst Ratio on the Pyrolysis Yields for Waste Tyre,” *Am. J. Chem. Eng.*, vol. 6, no. 4, p. 60, 2018.
- [52] B. Calvin H, “Mechanisms of Catalyst Deactivation,” *Chem. Eng. J.*, vol. 212, pp. 17–60, 2001.
- [53] LibreTexts, “Bond Energies,” *chem.libretexts.org*, 2020. [Online]. Available:

- https://chem.libretexts.org/Core/Physical_and_Theoretical_Chemistry/Chemical_Bonding/Fundamentals_of_Chemical_Bonding/Bond_Energies. [Accessed: 15-Jan-2021].
- [54] J. M. Technol, "Accessibility and Location of Acid Sites in Zeolites as Probed by Fourier Transform Infrared Spectroscopy and Magic Angle Spinning Nuclear Magnetic Resonance Understanding heterogeneous catalysts using probe molecule experiments," *technology.matthey.com*, 2018.
- [55] H. Nakabayashi, "Properties of Acid Sites on TiO₂-SiO₂ and TiO₂-Al₂O₃ Mixed Oxides Measured by Infrared Spectroscopy," *Bulletin of the Chemical Society of Japan*, vol. 65, no. 3. pp. 914–916, 1992.
- [56] V. L. Dagle, M. D. Flake, T. L. Lemmon, J. S. Lopez, L. Kovarik, and R. A. Dagle, "Effect of the SiO₂ support on the catalytic performance of Ag/ZrO₂/SiO₂ catalysts for the single-bed production of butadiene from ethanol," *Appl. Catal. B Environ.*, vol. 236, pp. 576–587, 2018.
- [57] L. Novikova, F. Roessner, L. Belchinskaya, M. AlSawalha, and V. Krupskaya, "Study of surface acid-base properties of natural clays and zeolites by the conversion of 2-methylbut-3-yn-2-ol," *Appl. Clay Sci.*, vol. 101, no. October, pp. 229–236, 2014.
- [58] A. Galadima and O. Muraza, "In situ fast pyrolysis of biomass with zeolite catalysts for bioaromatics/gasoline production: A review," *Energy Convers. Manag.*, vol. 105, pp. 338–354, 2015.
- [59] HIMEDIA, "Product Information Product Information," 2018.
- [60] engineersedge.com, "kinematic-viscosity-table," https://www.engineersedge.com/fluid_flow/kinematic-viscosity-table.htm, 2021. [Online]. Available: https://www.engineersedge.com/fluid_flow/kinematic-viscosity-table.htm. [Accessed: 18-Jan-2021].
- [61] PT. PERTAMINA (persero), "Spesifikasi Solar / Biosolar," no. 1, p. 17, 2017.
- [62] E. ToolBox, "fuels - densities specific volumes," https://www.engineeringtoolbox.com/fuels-densities-specific-volumes-d_166.html, 2003. [Online]. Available: https://www.engineeringtoolbox.com/fuels-densities-specific-volumes-d_166.html. [Accessed: 17-Jan-2021].
- [63] G. Tüccar, E. Tosun, and E. Uludamar, "Investigations of Effects of Density and Viscosity of Diesel and Biodiesel Fuels on NO_x and other Emission Formations," *Acad. Platf. J.*

- Eng. Sci.*, vol. 6, no. 2, pp. 81–85, 2018.
- [64] A. J. Wharton, *Diesel Engine Third Edition*, 3rd ed. Oxford, 2013.
- [65] Mckinsey, “Smoke point,” *www.mckinseyenergyinsights.com*. [Online]. Available: <https://www.mckinseyenergyinsights.com/resources/refinery-reference-desk/smoke-point/>. [Accessed: 23-Jan-2021].
- [66] J. G. Rankin and P. Harrington, “Development and Validation of a Method for Individualization of Middle Petroleum Distillates and Kerosene Ignitable Liquids,” no. 240686 / 2008-DN-BX-K146, p. 108, 2012.
- [67] W. N. Association, “Heat Values of Various Fuels,” *WorldNuclear.Org*, 2016. [Online]. Available: <https://www.world-nuclear.org/information-library/facts-and-figures/heat-values-of-various-fuels.aspx>. [Accessed: 17-Jan-2021].
- [68] AZoNano, “Silicon Dioxide (SiO₂) Nanoparticles – Properties & Applications,” 2013. [Online]. Available: <http://www.azonano.com/article.aspx?ArticleID=1381>.
- [69] R. E. Grim and N. Güven, *Developments in Sedimentology*, vol. 24. Elsevier Inc., 1978.
- [70] Z. International, “Safety Data Sheet ZSM-5,” 2014.
- [71] International Peer Reviewed Chemical Safety Information, “Kerosene,” *www.inchem.org*. [Online]. Available: <http://www.inchem.org/documents/icsc/icsc/eics0663.htm>.
- [72] ASTM International, “Standard Test Method for Heat of Combustion of Liquid Hydrocarbon Fuels by Bomb Calorimeter (reapproved 2007),” *ASTM Stand. D240-02*, vol. i, no. Reapproved, pp. 1–9, 2009.
- [73] U. N. B. of Standards, “Standard Test Methods for Specific Gravity, Apparent, of Liquid Industrial Chemicals,” pp. 1–2, 2017.
- [74] D. ASTM, “Standard Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (the Calculation of Dynamic Viscosity),” *Man. Hydrocarb. Anal. 6th Ed.*, pp. 126-126–8, 2008.