

## BAB V

### KESIMPULAN DAN SARAN

#### 5.1 Kesimpulan

Dari penelitian pengolahan limbah *film LDPE* menjadi bahan bakar cair menggunakan pelarut *stearin*, dapat ditarik kesimpulan bahwa :

1. Semakin tinggi temperatur yang digunakan, maka %*loss* yang dihasilkan akan semakin besar.
2. Semakin lama waktu reaksi berlangsung, maka %*loss* yang dihasilkan akan semakin besar.
3. Temperatur 295°C merupakan temperatur batas atas untuk percobaan menggunakan *stearin*, dikarenakan hasil sudah berbentuk padatan semua dan terdapat hasil yang gosong.
4. Variasi 295°C merupakan variasi temperatur terbaik, karena pada variasi 295°C ditemukan fraksi cair.

#### 5.2 Saran

Saran untuk penelitian pengolahan limbah *film LDPE* menjadi bahan bakar cair adalah :

1. Dapat dicoba kondisi operasi yang berada di antara 265°C dan 295°C untuk mendapatkan fraksi cair yang lebih besar.
2. Dapat dicoba waktu reaksi yang berada di antara 1 jam dan 2 jam untuk mendapatkan fraksi cair yang lebih besar.
3. Dapat dicoba untuk menganalisis pengaruh pengotor pada plastik terhadap fraksi cair yang dihasilkan

## DAFTAR PUSTAKA

- Adoe, D. G. H., Bunganaen, W., Krisnawi, I. F., & Soekwanto, F. A. (2016). Pirolisis Sampah Plastik PP (Polypropylene) menjadi Minyak Pirolisis sebagai Bahan Bakar Primer. *LONTAR Jurnal Teknik Mesin Undana*, 3(1), 17–26.
- Akhbar, T. (2013). Pengaruh Penambahan Zat Aditif Octane Boster Pada Bahan Bakar Premium Terhadap Kandungan Emisi Gas Buang Pada Sepeda Motor Honda Vario Tecno 110 CC. *Jurnal Penelitian*, 3(2), 11.
- Arief, L. M. (2016). *Pengolahan Limbah Industri Dasar-Dasar Pengetahuan dan Aplikasi di Tempat Kerja* (E. Risanto (Ed.)). ANDI.
- Bagri, R., & Williams, P. T. (2002). Catalytic pyrolysis of polyethylene. *Journal of Analytical and Applied Pyrolysis*, 63(1), 29–41. [https://doi.org/10.1016/S0165-2370\(01\)00139-5](https://doi.org/10.1016/S0165-2370(01)00139-5)
- Bahraini, A. (2018). 7 Tipe Plastik yang Perlu Anda Ketahui. <https://waste4change.com/blog/tipe-plastik/>
- Bhutto, N., Cagatay, S., (2023). Controlling Greenhouse Gases Emissions via Natural Gas Substitution: An Input-Output Study for Turkey.
- Buekens, A. G., & Huang, H. (1998). Catalytic plastics cracking for recovery of gasoline-range hydrocarbons from municipal plastic wastes. *Resources, Conservation and Recycling*, 23(3), 163–181. [https://doi.org/10.1016/S0921-3449\(98\)00025-1](https://doi.org/10.1016/S0921-3449(98)00025-1)
- Cahyono, M. S., & Ika Fenti, U. (2017). Influence of Heating Rate and Temperature on the Yield and Properties of Pyrolysis Oil Obtained from Waste Plastic Bag. *Conserve: Journal of Energy and Environmental Studies*, 1(1), 1–8. <https://doi.org/10.30588/cjees.v1i1.248>
- Catalogue, P. (2017). *Low Density Polyethylene Why To Choose*.
- Dewi, K. I. N., Prasetya, A., Faculty, E., Mada, U. G., Faculty, E., & Mada, U. G. (2015). Characteristics of Pyrolysis Oil Batch Polyethylene and Polystyrene Plastic Waste. *Journal UGM*, 73–77. <http://journal.ugm.ac.id/index.php/ajse>
- Dharma, U. S., Nugroho, E., & Fatkuahman, M. (2018). Analisa Kinerja Mesin Diesel Berbahan Bakar. *Jurnal Teknik Mesin Univ. Muhammadiyah Metro*, 7(1), 1–10.
- Editor John Scheirs, S., & Polyesters, M. (2006). *Wiley Series in Polymer Science Metallocene-based polyolefins Preparations, Properties and Technology Polymer-Clay Nanocomposites Dendrimers and Other Dendritic Polymers Modern Styrenic Polymers Polystyrenes and Styrenic Copolymers Forthcoming Titles Ligh*.
- Engineering, P. (2010). *Pyrolysis of Waste Plastics into Fuels By Feng Gao*.
- Fadillah, F. A., & Tjandra, F. (2019). *Pengolahan Limbah Ldpe Menjadi Bahan Bakar Cair*.

- Geyer, R., Jambeck, J. R., & Law, K. L. (2017). Production, use, and fate of all plastics ever made. *Science Advances*, 3(7), 25–29. <https://doi.org/10.1126/sciadv.1700782>
- Goad, M. A., Ali, R., Goad, M. A., Thermal, R. A., & Cracking, C. (2017). *Thermal and Catalytic Cracking of Plastic Wastes into Hydrocarbon Fuels To cite this version : HAL Id : hal-01571289 Thermal and Catalytic Cracking of Plastic Wastes into Hydrocarbon Fuels.*
- Gusniar, I. N. (2018). Metode Pembuatan Paving Block Segi Enam Berbahan Sampah Plastik Dengan Mesin Injection Molding. *Jurnal Barometer*, 3(2), 130–133.
- Iswadi, D., Nurisa, F., & Liastuti, E. (2017). Pemanfaatan sampah plastik LDPE dan PET menjadi bahan bakar minyak dengan proses pirolisis. *Jurnal Ilmiah Teknik Kimia UNPAM*, 1(2), 1–9. [openjournal.unpam.ac.id/index.php/JITK/article/download/718/585](http://openjournal.unpam.ac.id/index.php/JITK/article/download/718/585)
- Juwono, H., Tri Sujadmiko, M., Fauziah, L., & Ayyun, I. (2019). Catalytic Conversion From Plastic Waste by Silica-Alumina-Ceramic Catalyst to Produce an Alternative Fuel Hydrocarbon Fraction. *Jurnal ILMU DASAR*, 20(2), 83-88. doi:10.19184/jid.v20i2.8829
- Kumar, B., Sadagopan, R. S., Pandu Vasanthi, R., Kalapati, M., & Vishnuvardhan, M. (2013). Comparative physico-chemical, proximate and mineral analysis on raw and roasted seeds of groundnut. *Communications in Plant Sciences*, 3(June), 3–4.
- Kumar, S., Panda, A. K., & Singh, R. K. (2011). A review on tertiary recycling of high-density polyethylene to fuel. *Resources, Conservation and Recycling*, 55(11), 893–910. <https://doi.org/10.1016/j.resconrec.2011.05.005>
- Kunwar, B., Cheng, H. N., Chandrashekaran, S. R., & Sharma, B. K. (2016). Plastics to fuel: a review. *Renewable and Sustainable Energy Reviews*, 54, 421–428. <https://doi.org/10.1016/j.rser.2015.10.015>
- Lebreton, L., & Andrade, A. (2019). Future scenarios of global plastic waste generation and disposal. *Palgrave Communications*, 5(1), 1–11. <https://doi.org/10.1057/s41599-018-0212-7>
- Liestiono, R. P., Cahyono, M. S., Widyawidura, W., Prasetya, A., & Syamsiro, M. (2017). Karakteristik Minyak dan Gas Hasil Proses Dekomposisi Termal Plastik Jenis Low Density Polyethylene (LDPE). *Jurnal Offshore: Oil, Production Facilities and Renewable Energy*, 1(2), 1. <https://doi.org/10.30588/jo.v1i2.288>
- Li-Na, J. (2013). Study on preparation process and properties of polyethylene terephthalate (pet). *Applied Mechanics and Materials*, 312, 406–410. <https://doi.org/10.4028/www.scientific.net/AMM.312.406>
- Mahmudha, S., & Nugraha, I. (2016). Pengaruh Penggunaan Bentonit Teraktivasi Asam Sebagai Katalis Terhadap Peningkatan Kandungan Senyawa Isopulegol Pada Minyak Sereh Wangi Kabupaten Gayo Lues – Aceh. *Chimica et Natura Acta*, 4(3), 123. <https://doi.org/10.24198/cna.v4.n3.10921>

- Martinez, I. (1992), "Termodinámica básica y aplicada", Ed. Dossat, 1992, ISBN 84-237-0810-1, Bab 15 hlm 4-5.
- Miandad, R., Barakat, M. A., Aburiazaiza, A. S., Rehan, M., & Nizami, A. S. (2016). Catalytic pyrolysis of plastic waste: A review. *Process Safety and Environmental Protection*, 102, 822–838. <https://doi.org/10.1016/j.psep.2016.06.022>
- Nugroho, A. S. (2020). Pengolahan Limbah Plastik Ldpe Dan Pp Untuk Bahan Bakar Dengan Cara Pirolisis. *Jurnal Litbang Sukowati : Media Penelitian Dan Pengembangan*, 4(1), 10. <https://doi.org/10.32630/sukowati.v4i1.166>
- Onwudili, J. A., Insura, N., & Williams, P. T. (2009). Composition of products from the pyrolysis of polyethylene and polystyrene in a closed batch reactor: Effects of temperature and residence time. *Journal of Analytical and Applied Pyrolysis*, 86(2), 293–303. <https://doi.org/10.1016/j.jaap.2009.07.008>
- Panda, A. K., Alotaibi, A., Kozhevnikov, I. V., & Shiju, N. R. (2020). Pyrolysis of Plastics to Liquid Fuel Using Sulphated Zirconium Hydroxide Catalyst. *Waste and Biomass Valorization*, 11(11), 6337–6345. <https://doi.org/10.1007/s12649-019-00841-4>
- Patrik, S. G. (2005). *Practical Guid to Polyvinyl Chloride*. Rapra Technology Limited. <http://www.rapra.net>
- Penelitian, L., Fadillah, F. A., Tjandra, F., & T, T. H. S. (2021). *BAHAN BAKAR CAIR DENGAN CATALYTIC*.
- Quesada, L., de Hoces, M. C., Martín-Lara, M. A., Luzón, G., & Blázquez, G. (2020). Performance of different catalysts for the in situ cracking of the oil-waxes obtained by the pyrolysis of polyethylene filmwaste. *Sustainability (Switzerland)*, 12(13), 1–15. <https://doi.org/10.3390/su12135482>
- Renilaili, R. (2019). Bahan Bakar Cair Dari Limbah Plastik Dengan Metode Catalytic Cracking. *Jurnal Tekno*, 16(2), 12–22. <https://doi.org/10.33557/jtekno.v16i1.621>
- Ridhuan, K., Irawan, D., & Inthifawzi, R. (2019). Proses Pembakaran Pirolisis dengan Jenis Biomassa dan Karakteristik Asap Cair yang Dihasilkan. *Turbo : Jurnal Program Studi Teknik Mesin*, 8(1), 69–78. <https://doi.org/10.24127/trb.v8i1.924>
- Rima Riyanti, Ulinnuha Latifa, Y. S. (2021). *Multitek Indonesia : Jurnal Ilmiah*. 6223(January), 121–130.
- Sakthivel, G., Nagarajan, G., Ilangkumaran, M., & Gaikwad, A. B. (2014). "Comparative analysis of performance, emission and combustion parameters of diesel engine fuelled with ethyl ester of fish oil and its diesel blends" Fuel, 132, 116–124. doi:10.1016/j.fuel.2014.04.059
- Selpiana, Selpiana & Susmanto, Prahady & Cundari, Lia & Putri, Rizka & Ibrahim, Omar & Oktari, Dedek. (2019). KONVERSI LIMBAH PLASTIK JENIS EXPANDED

- Serrano, D. P., Aguado, J., Escola, J. M., & Garagorri, E. (2003). Performance of a continuous screw kiln reactor for the thermal and catalytic conversion of polyethylene-lubricating oil base mixtures. *Applied Catalysis B: Environmental*, 44(2), 95–105. [https://doi.org/10.1016/S0926-3373\(03\)00024-9](https://doi.org/10.1016/S0926-3373(03)00024-9)
- Shah, A. T., Mujahid, A., Farooq, M. U., Ahmad, W., Li, B., Irfan, M., & Qadir, M. A. (2012). Micelle directed synthesis of (C 19H 42N) 4H 3(PW 11O 39) nanoparticles and their catalytic efficiency for oxidative degradation of azo dye. *Journal of Sol-Gel Science and Technology*, 63(1), 194–199. <https://doi.org/10.1007/s10971-012-2779-6>
- Singh, S., Prakash, C., Ramakrishna, S., & Krolczyk, G. (2010). Advances in Materials Processing IX. In *Key Engineering Materials* (Vol. 443).
- Sumingkrat. (2002). TERBENTUKNYA DIOKSIN AKIBAT REAKSI KIMIA PADA PROSES PEMBAKARAN DAN DAMPAKNYA BAGI MANUSIA. *BULLETIN PENELITIAN*, XXIV(1).
- Syamsiro, M., Saptoadi, H., Norsujianto, T., Noviasri, P., Cheng, S., Alimuddin, Z., & Yoshikawa, K. (2014). Fuel oil production from municipal plastic wastes in sequential pyrolysis and catalytic reforming reactors. *Energy Procedia*, 47, 180–188. <https://doi.org/10.1016/j.egypro.2014.01.212>
- Tripathi, D. (2002). *Practical Guide to Polypropylene*. Rapra Technology Limited. <http://www.rapra.net>
- Wahyono. (2019). 10 Negara Eskportir Sampah Plastik Terbanyak ke Indonesia. *SINDONEWS*. <https://ekbis.sindonews.com/berita/1424082/34/10-negara-eksportir-sampah-plastik-terbanyak-ke-indonesia/10>
- Wijayanto, D. S., Rohman, N., Ranto, R., Bugis, H., Nurachman, A., & Nugroho, F. A. (2017). Analisis Penerapan Heat Transfer Pada Pemanasan Bahan Bakar Bensin Melalui Pipa Kapiler Bersirip Radial Di Dalamupper Tank Radiator Untuk Meningkatkan Performansi Mesin Kijang. *Jurnal Ilmiah Pendidikan Teknik Dan Kejuruan*, 6(2), 76–92. <https://doi.org/10.20961/jiptek.v6i2.12556>
- Wiratmaja, I. (2010). Pengujian Karakteristik Fisika Biogasoline Sebagai Bahan Bakar Alternatif Pengganti Bensin Murni. *Jurnal Energi Dan Manufaktur*, 4(2).
- Wong, S. L., Ngadi, N., Abdullah, T. A. T., & Inuwa, I. M. (2017). Conversion of low density polyethylene (LDPE) over ZSM-5 zeolite to liquid fuel. *Fuel*, 192, 71–82. <https://doi.org/10.1016/j.fuel.2016.12.008>
- Zattini, G., Leonardi, C., Mazzocchetti, L., Cavazzoni, M., Montanari, I., Tosi, C., Benelli, T., & Giorgini, L. (2017). Pyrolysis of low-density polyethylene. *Smart Innovation, Systems and Technologies*, 68, 480–490. [https://doi.org/10.1007/978-3-319-57078-5\\_46](https://doi.org/10.1007/978-3-319-57078-5_46)